

REMARKS

This Preliminary Amendment is to correct typographical errors in the specification. Both the errors and the corrections are clear. No new matter has been added.

Applicant respectfully requests favorable consideration and early passage to issue of the present case.

Applicant's undersigned attorney may be reached in our New York office by telephone at (212) 218-2100. All correspondence should continue to be directed to our address given below.

Respectfully submitted,



Attorney for Applicant

Registration No. 48,512

FITZPATRICK, CELLA, HARPER & SCINTO
30 Rockefeller Plaza
New York, New York 10112-3801
Facsimile: (212) 218-2200



APPENDIX

Application No.: 10/055,973
Attorney Docket No.: 03500.016125

IN THE SPECIFICATION:

The paragraph beginning at page 11, line 16, and ending at page 11, line 23,
has been amended as follows:

ΔE_{ab}^* is prescribed in the following manner in JIS K 7105. $\Delta E_{ab}^* = \{(\Delta L^*)^2 + (\Delta a^*)^2 + (\Delta b^*)^2\}^{1/2}$. Incidentally, ΔE_{ab}^* indicates a color difference between two color stimulus values, which is defined by a difference, ΔL^* , Δa^* , Δb^* in a coordinate, L^* , a^* , b^* in the $L^*a^*b^*$ color space determined by CIE (International Commission on Illumination) in 1976.

RECEIVED
APR 09 2002
TC 1700

The paragraph beginning at page 12, line 10, and ending at page 12, line 14,
has been amended as follows:

The type and amount of a flame retardant to be added are determined according to the flame-retardant level required and a main resin material used, and UL 94 (Underwriter Laboratory [94]) is generally known as a standard for flame retardance.

The paragraph beginning at page 16, line 2, and ending at page 16, line 14,
has been amended as follows:

RECEIVED
APR 25 2002
TC 1700

The ground product after the washing is preferably dried to a water content of at most 0.3 % by mass by means of a centrifugal dehydration [dehydration] system. When the water content is at most 0.3% [3 %] by mass, a possibility that the ground product which has become flaky may be stuck on each other becomes low, and so operability can be improved. In addition, deterioration of the ABS resin by hydrolysis can be prevented. Further, the washing time is shortened compared with a filtration process using a filter or the like, and deterioration of color tone of the finally obtained recycled ABS resin can also be prevented.